

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING OF DIAMOND AND COLORED STONES **EDUCATIONAL PROGRAMS**

> Expertise issued by I.G.I byba Head Office and Laboratories.

1/7 Schupstraat, 2018 Antwerp - Belgium Tel. +32 3 401 08 88 - Fax +32 3 232 07 58 E-mail: info@igiworldwide.com www.igiworldwide.com

DIAMOND REPORT

This report is a statement of the diamond's identity and grade including all relevant information.

NUMBER

F1R23573

ANTWERP, April 13, 2014

LABORATORY REPORT (ORIGINAL)

TO WHOM IT MAY CONCERN.

DESCRIPTION SHAPE AND CUT

CARAT WEIGHT COLOR GRADE CLARITY GRADE CUT GRADE

POLISH SYMMETRY

Table

Measurements

Crown Height - Angle

Pavilion Depth - Angle

Girdle Thickness

Culet

FLUORESCENCE

NATURAL DIAMOND

ROUND BRILLIANT

1.00 CARAT

SI 2 GOOD

GOOD GOOD

6.11 - 6.13 x 4.08 mm

55.5%

17.5% - 38°

42.5% - 40.3°

THICK TO VERY THICK (FAC.)


MEDIUM


NONE

The symbols do not usually reflect the size of the characteristics

Red symbols indicate internal characteristics.

Green symbols indicate external characteristics.





insignificant external details, visible under high magnification only, are not shown



O-ms Security features included in this document are hologram. watermarked paper and additional features not listed. that, as a composite, exceed industry security standards.

CLARITY GRADE:

Internally Flawless

COLOR GRADE : D

G

K J

0

Q

S-Z

FANCY COLOR

PROPORTION - MARGIN: ± 1%

MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years' experience in this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report IGI does not agree to purchase or replace the article. Neither IGI nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.